

RESURF® RESIN AS PRIMER COAT

“A SMALL BUT VERY SIGNIFICANT CHANGE”

BOND STRENGTH AND FREEZE/THAW PERFORMANCE OF RESURF RESIN USED AS PRIMER CAN (AND SHOULD BE) ENHANCED BY SIMPLY MIXING FLEXIBILIZING, SHRINK CONTROL ADDITIVE INTO PRIMER. PRIMER (AND ALL RESIN USED) IS CATALYZED AS ALWAYS. AFTER THE PORTLAND CEMENT CONCRETE TO BE REPAIRED HAS BEEN PRIMED, RESURF II POLYMER CONCRETE CAN BE PLACED WHILE STILL WET OR MANY HOURS LATER.

PRIMER ADDITIVE DIRECTIONS FOR USE

- RATIO: FOR APPROX. ½ GAL. RESURF RESIN USE APPROX.1 CUP (PROVIDED)
- MIX IN (DISPERSE SOMEWHAT) ALL LUMPS WILL NOT BREAK UP NOR DISSOLVE. THIS IS OK
- CATALYZE AS ALWAYS (RATIO: ONE MARK ON MEASURING BOTTLE TO ONE GALLON RESURF RESIN – NOTE COLOR CHANGE
- APPLY WITH PAINT BRUSH – PAINT OUT PUDDLES
- FILL HOLE WITH RESURF II POLYMER CONCRETE (SEE BAG DIRECTIONS)

NOTE: PRIMER BATCH SIZES CAN EASILY BE RATIOED UP OR DOWN TO SAVE PRIMER RESIN OR TIME

CALL: 334-682-4296 OR 334-412-2440 FOR HELP: THANX